



KBS TOP COATER

AEROSOL DIRECTIONS & APPLICATION INFORMATION

KBS TOP COATER

KBS Top Coater is a superior aerosol spray paint formulated for maximum coverage and professional looking results.

KBS Top Coater is an ideal top coat paint for RustSeal when the area will be consistently exposed to sunlight.

KBS Top Coater is a very high solids paint does not run or sag, and gives at least twice the coverage of conventional spray paints.

To achieve expert results, please take the time to carefully read and understand the following directions before you begin your restoration project. If you have any remaining questions or concerns, please call us toll-free for technical assistance.

ALWAYS WORK IN A WELL-VENTILATED AREA. A NIOSH/MSHA APPROVED AIR SUPPLIED RESPIRATOR IS RECOMMENDED. ALWAYS WEAR PROTECTIVE GLOVES AND EYEWEAR.

THEORETICAL COVERAGE:

16oz can of KBS Top Coater should coat up to 38 sq. ft. with 1 coat coverage.

12oz can of KBS Top Coater should coat up to 30 sq. ft. with 1 coat coverage.

SURFACE PREP:

FOR THE BEST END RESULTS, apply KBS Top Coater to clean & dry surfaces that have been permanently sealed with RustSeal. If needed, use KBS Klean to remove all surface contaminants. (Avoid solvent-based cleaners which leave invisible residues that can affect the adhesion of KBS Top Coater.) To topcoat freshly painted RustSeal surfaces (between 3 and 8 hours old), apply KBS Top Coater directly as no other prep is required. For all other applications, lightly sand/scuff with 320 grit paper then clean & dry surface before applying KBS Top Coater.

SPRAY APPLICATION:

For best results, Apply KBS Top Coater to prepared surfaces as described above. ALWAYS WEAR PROTECTIVE GLOVES AND EYEWEAR when using KBS Top Coater. Always use NIOSH/MSHA approved air supplied respirator. For best results, spray at room temperature 50° to 90°F (10° to 32°C). Use only in moderate to dry atmospheric conditions (i.e. 70% humidity or lower). Shake can for at least one minute after listening for rattle or mixing ball. During application, shake intermittently for approximately 10 seconds at 1 to 2 minute intervals. Press valve all the way down. Do not extend finger beyond the valve. Hold container about 8 to 10 inches from surface to be sprayed. Do not cover with continuous spray. Move back and forth, releasing sprayhead after stroke. Overlap each stroke.

If clogging develops, turn sprayhead 1/4 turn or remove and

clean sprayhead. Do not stick pin or other objects in to can opening. With sprayhead pointed away from you, reinsert sprayhead with gentle twisting motion.

IMPORTANT: Apply thin coats rather than heavy coats. If paint runs or sags, paint is being applied too heavily or paint can is too close to surface. Apply one or two thin covering coats for general automotive applications. For marine or industrial applications, apply a minimum of 2-3 thin covering coats. Recoating can be done once first or consecutive coat is dry-to-touch. For best results, always apply coats consecutively within 24 hours of each coat curing. Average recoat cure times are 1-2 hours depending on humidity levels. Full cure is usually achieved within 24 hours but can take up to 7 days.

To clear sprayhead for future use, turn can upside down and spray for 3 seconds.

CLEAN UP:

Clean up any overspray with KBS #1 Thinner or lacquer thinner immediately. Always wear protective gloves to avoid skin contact and temporary staining.

Please remember these instructions are general guidelines only and do not cover every application and environment. If you remain unsure as how to proceed, refer to product instruction sheet, our website: **KBS-Coatings.com**, or call for technical advice at **1-219-263-0073**.

Please follow all warning and caution notices. See SDS for additional information.

MADE IN THE USA.

Information contained herein is to our knowledge true and accurate, but all recommendations or suggestions are made without guarantee. Since application lies outside our control, we cannot accept any liability for the results. User shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.

KBS SUPPORT FORUM

SUCCESS.KBS-COATINGS.COM

COMPLETE HOW-TO'S

KBS-COATINGS.COM

KBS ONLINE INSTRUCTIONAL VIDEOS

VIEW 3-STEP SYSTEM APPLICATION VIDEOS
AVAILABLE ON KBS-COATINGS.COM